

Product Description

TREMproof® 250GC is a rapid-curing, high-solids, VOC-compliant modified polyurethane waterproofing membrane that can be applied to damp and green concrete. TREMproof 250GC is a one-part moisture-curing elastomer available in three viscosities: Self-Leveling (SL), Roller (R) and Trowel (trowel intended for detailing work only).

Basic Uses

TREMproof 250GC is designed for use on backfilled walls, split slab applications, planters and submerged conditions.

Features and Benefits

- TREMproof 250GC can be applied in as little as 24 hours following the removal of concrete forms. It can also be applied to damp concrete, reducing the delays associated with rain or other sources of moisture.
- The unique ability to catalyze TREMproof 250GC-SL with water when desired will speed cure times, especially in cold temperatures and low relative humidity, to further condense the construction schedule.
- TREMproof 250GC can be applied at a rate of up to 120 mils in a single lift to speed application without sacrificing performance.
- It can also be applied in multiple lifts to achieve a 215-mil high-build system when maximum protection is required.

Availability

Immediately available from your local Tremco Sales Representative or Distributor. For Distributor locations, visit www.tremcosealants.com.

Coverage Rates

Approximately 25 ft²/gal (0.61 M²/L) at 60 wet mils

Approximately 18 ft²/gal (0.44 M²/L) at 90 wet mils

Approximately 13 ft²/gal (0.32 M²/L) at 120 wet mils

Approximately 7.5 ft²/gal (0.19 M²/L) at 215 wet mils

Packaging

5-gallon (19-L) pails, 36 pails/pallet

55-gallon (208-L) drums, 4 drums/pallet

Applicable Standards

TREMproof 250GC meets or exceeds the following specifications:

- ASTM C836 Standard Specifications for High Solids Content, Cold Liquid-Applied Elastomeric Waterproofing Membrane for Use with Separate Wearing Course
- City of Los Angeles (COLA) approval standards
- Miami-Dade County Acceptance

Limitations

- Do not apply to contaminated surfaces.
- Not to be used as an exposed or wearing surface.
- Use with adequate ventilation.
- Concrete forms must be removed a minimum of 24 hours before TREMproof 250GC can be applied.
- Not approved for direct contact with asphalt-based products.
- Not for use with potable water.
- Contact your local Tremco Sales Representative or Tremco Technical Service for compatibility information and job-specific recommendations on tie-in and termination details.
- Do not apply over a curing or forming oil compound.
- Do not apply over a non-vented substrate without contacting your local Tremco Sales Representative.

Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	DESCRIPTION	
Composition	Modified Polyurethane Waterproofing	
Color	Black	
Solids	No less than 84%*	
Grade(s)	Trowel, Roller and Self-Leveling	
Cure Time	6 to 12 hr at 75 °F (24 °C), 50% RH	
Thickness	60 mils	
PROPERTY	TEST METHOD	TYPICAL VALUES
Film Thickness	ASTM C836	60 wet mils
Adhesion-in-Peel after Water Immersion (Unprimed)	ASTM C836; ASTM C 794	17 lbf/in (29.77 N/cm)
Low-Temp Flexibility	ASTM C836; ASTM C 836	Pass
Weight Loss 20% maximum Loss 80% Solids minimum	ASTM C836; ASTM C 1250	16% Loss maximum 84% Solids minimum
Low Temperature Crack Bridging	ASTM C836; ASTM C1305	Pass
Extension after heat aging No observable cracking	ASTM C836; ASTM C1522	Pass
Hardness, Type 00 50 Min.	ASTM C836; ASTM D 2240	87
Water Vapor Permeance	ASTM C836; ASTM E96 Dry Cup	
	ASTM C836; ASTM E96 Wet Cup	1.15 US Perms
	ASTM C836; ASTM E96 Inverted Wet Cup	1.05 US Perms
Maximum V.O.C.	Method 310	No more than 177 g/L* (LV formulation does not exceed 100 g/L)
Shelf Life Stability 6 Months Minimum		Pass
Application Temperature		Above 40 °F (5 °C) and rising. If installing below 40 °F (5 °C), please contact Tremco Technical Services at 866-209-2404.
Storage Temperature		40 to 100 °F (5 to 37 °C)

*Varies Depending on grade of material used.

**Modified ASTM C1305

0116/TP250GCDS-BG

Tremco Commercial Sealants & Waterproofing

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555

