

### Product Description

Vulkem® 350NF/951NF is a composite waterproofing system comprised of tough-curing liquid polyurethane. It cures to form a rubber membrane surface that provides a lasting and easy-to-clean coating. Textured surfaces for pedestrian traffic will use an aggregate-laden top membrane to aid in wear and slip resistance. Vulkem 350NF/951NF may be used to apply a seamless, monolithic waterproof membrane to concrete, well-anchored AC plywood, and primed metal surfaces.

Vulkem 350NF Base Coat is a single-component, low odor, low VOC, urethane membrane that bonds firmly to clean, dry concrete, plywood and metal. It retains its integrity even if substrate movement causes hair-line cracks of up to 1/16" (1.5 mm). If cut or damaged, Vulkem 350NF will prevent water migration between itself and the substrate. Vulkem 350NF is available in roller (R) and in self-leveling (SL) grade for vertical and horizontal application.

Vulkem 951NF Top Coat is an aliphatic, two-component, polyurethane, which when used in conjunction with the recommended aggregate, creates a tough, aesthetically appealing, skid resistant, wearing surface that forms a strong interlaminar bond to the Vulkem 350NF basecoat.

### Basic Uses

Vulkem 350NF/951NF is ideal for plazas, recreation decks, balconies, mechanical rooms, stadiums, athletic surfaces, and similar applications requiring an elastomeric waterproofing system.

### Features and Benefits

- Fast cure through time allows for use 12 hr after installation.
- Low odor and low level of Volatile Organic Compounds (VOC) allow for use in neighbor friendly, inhabited structures.
- Mildew- and fungus- resistance safeguards concrete surfaces against environmental contaminants.
- Excellent durability and UV resistance extend the useful life of pedestrian systems.
- Re-coatability and compatibility with other Tremco sealants enhance waterproofing protection with full system compatibility.

### Availability

Immediately available from your local Tremco Sales Representative, Tremco distributor, or warehouse.

### Packaging

Vulkem 350NF: 5-gal (18.9-L) pails, 55-gal (208.2-L) drums

Vulkem 951NF: Total of 4.6-gal kit – Part A 3.75 gal (14.2 L) in a 5-gal (18.9-L) pail, Part B 0.85 gal (3.2 L) in a 1-gal pail

### Colors

Vulkem 951NF is available in Beige, Gray, Limestone, Black and Slate Gray. Special colors are available upon request.

### Installation

Concrete shall be water-cured and attain a 3000 psi minimum compressive strength. Concrete finish shall be a light steel trowel followed by a fine-hair broom, or equivalent ICRI #2-#4 finish. Moisture content in the concrete must be lower than 4.5% as measured using a Tramex CME 4 Moisture Meter. Depending on concrete construction and job site location, additional concrete testing may be required. Please contact your local Tremco Sales or Technical Representative.

Please refer to the Vulkem 350NF/951NF Application Instructions for complete application details. The techniques involved may require modification to adjust to the jobsite conditions. Consult your Tremco Sales Representative or Tremco Technical Services for site conditions and requirements.

### Applicable Standards

Conforms to ASTM C957. Conforms to UL 790 - Class A Rating for non-combustible substrates

### Limitations

- Do not apply to damp or contaminated surfaces.
- Use with adequate ventilation.

### Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.

**TYPICAL PHYSICAL PROPERTIES**

PROPERTY	TEST METHOD	VULKEM 350NF	VULKEM 951NF
Flash Point	Set-A-Flash	>160 °F (71 °C)	>200 °F (93 °C)
% Solids (by Weight)	ASTM D1353	90 to 98%	80 to 85%
Drying Time @ 75 °F, 50% RH	ASTM D1640	40 mil film, 4 to 6 hr	12 mil film, 2 to 4 hr
Open to foot traffic		N/A	12 hr after cure
Weathering	ASTM D822	N/A	No effect
Salt Spray	ASTM B117	N/A	No effect
Viscosity	Brookfield C&P	4000 to 6000 cps	2500 cps
Elongation	ASTM D412	600 to 700%	145%
Tensile Strength	ASTM D412	220 to 460 psi	4500 psi
Hardness (Shore A)	ASTM D2240	45 to 60	50 shore D
Adhesion (Peel Strength)	ASTM D903	Unprimed Concrete, 20 to 30 pli, 100% cohesive failure	100% cohesive failure
Adhesion (Pull-Off)	ASTM D4541	200 to 400 psi	200 to 400 psi
Abrasion Resistance (1000 cycles)	ATSM D4060	N/A	33 mg
Accelerated Aging	ASTM D573	No loss of elongation or tensile strength	No loss of elongation or tensile strength

\* Accelerated aging test. 1 daily cycle of UV and water spray greatly exceeds 1 day of real world exposure. Contact Tremco Technical Service or your local sales representative for more information.

**0815/350NF/951NFDS-DC**

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.



**Tremco Commercial Sealants & Waterproofing**

3735 Green Rd  
Beachwood OH 44122  
216.292.5000 / 800.321.7906

1451 Jacobson Ave  
Ashland OH 44805  
419.289.2050 / 800.321.6357

220 Wicksteed Ave  
Toronto ON M4H1G7  
416.421.3300 / 800.363.3213

1445 Rue de Coulomb  
Boucherville QC J4B 7L8  
514.521.9555