

Prefere 6718,Prefere 6730,Prefere 6732,Prefere 6735

Model	Prefere 6718	Prefere 6730	Prefere 6732	Prefere 6735
Application	Plate furniture and other parts of the automatic sealing edge and soft forming.Such as PVC, decorative paper, veneer, ABS and other sealing sapwood affixed to particleboard or MDF	Plate furniture and other parts of the automatic sealing edge and soft forming.Such as PVC, decorative paper, veneer, ABS and other sealing sapwood affixed to particleboard or MDF	Plate furniture and other parts of the automatic sealing edge and soft forming.Such as PVC, decorative paper, veneer, ABS and other sealing sapwood affixed to particleboard or MDF	Plate furniture and other parts of the automatic sealing edge. Such as PVC, decorative paper, veneer, ABS and other sealing sapwood affixed to particleboard or MDF.
characteristic	Ethylene copolymer. Medium viscosity, high bonding strength, good heat resistance. Less filler	Ethylene copolymer. Medium and low viscosity, high bonding strength, good heat resistance, long opening time	Ethylene copolymer. High bonding strength and good heat resistance.	Ethylene copolymer. Low viscosity, high bonding strength, good heat resistance. Especially for PVC as edge-sealing materials, the better the process effect
appearance	Micro-yellow particles	Micro-yellow particles	Micro-yellow particles	Micro-yellow particles
viscosity	60,000 ± 10,000 mPa.s	70,000 ± 10,000 mPa.s	130,000 ± 10,000 mPa.s	80,000 ± 10,000 mPa.s
softening point	108 ± 3 °C	100 ± 3 °C	108 ± 3 °C	101 ± 3 °C
density	~1.14 g/cm ³	1.46 g/cm ³	~ 1.31g/cm ³	~ 1.24 g/cm ³
Water Absorption Ration	8-10%	8-10%	8-10%	8-10%
ambient temperature	>15 °C	>15 °C	>15 °C	>15 °C
Glue temperature	150-200 °C	180-200 °C	180-200 °C	170-190 °C
Glue roller temperature	150-200 °C	190-210 °C	200-220 °C	190-210 °C
Roller Pressure	3-5 kg/cm ²	3-5 kg/cm ²	3-5 kg/cm ²	3-5 kg/cm ²
Feeding speed	18-30 m/min	≥12 m/min	18-30 m/min	18-35 m/min
coated weight	180-250 g/m ²	180-250 g/m ²	180-250 g/m ²	180-250 g/m ²
explanation	The nature of the sapwood and the use of the environment will affect the use of the effect, it is recommended that the user on the field test.			
clean	The residual glue is cleaned out periodically to prevent the thickness of the wall from affecting the heat transfer.			
storage life	Cool and dry place sealed for 2 years.			

Packing	25KG/bag.
---------	-----------